



DURAM PTY LTD
(INCORPORATING DURAMAX)
A.B.N. 50 612 836 718



To: Ecobuild Solutions

Att: Herbert Klintworth

By email: h.klintworth@ecobuildsolutions.com.au

To whom it my Concern,

Tests have been carried out on the adhesion of or Duram Primers, WB Primer, Superprime 711 and Azcoseal, on your Eco-Easy Panels.

Test undertaken at Huntsman Laboratory. All primers where allowed to fully cure and using Super strength Epoxy, Dolly's where adhered and allowed to cure for 2 days.

Generally, considering any result over 1.0 MPa as being acceptable. The following results on average over 3 individual tests each were achieved.

Results

Superprime: 1.69 Mpa

Azcoseal: 1.97 Mpa

WB Primer: 1.49 Mpa

Duram recommends the following systems to be applied over a properly prepared, sound and stable Eco-Easy Panel substrate.

Primer	Waterproofing Membrane
WB Primer	Durabit Reo, Durabit EF
Superprime 711	Durabit Reo, Durabit EF, Multithane STD or HV
Azcoseal	Durabit Reo, Durabit EF, Multithane STD or HV

Reference should be made to the relevant Product Data Sheet or AS3740:2004 for information not specifically covered in this letter.

Please feel free to pass on my mobile, so you or the applicator's can contact me directly for special pricing relating to any Eco-Easy Paneling projects.

Regards

Iain M^cLennan
Sales & Onsite Technical Support
Mob: 0419147954

• LIQUID WATERPROOFING MEMBRANES • ANTI-SLIP TRAFFICABLE, TEXTURE & FLOOR COATINGS • CONCRETE/MASONRY • SEALANTS •